



# Technical Data Sheet

## PVDF Pellet DH-F22M

DH-F22M is a kind of pellet PVDF; has high melting viscosity and suitable for making various PVDF products through compression molding. Products made from DH-F22M have a wide range of service temperature (-50°C to 150°C).

### Typical Properties::

Item	Unit	Specification	ASTM Test standard
Appearance	/	White and semi-transparent pellets	/
S.S.G	/	1.75~1.79	ASTM D792, @23/23°C
Melting Point	°C	165~171	ASTM D3418, 10°C/min
MFR	g/10min	1~5	ASTM D1238, 230°C/5kg
Water absorption	%	≤0.05	ASTM D570
Tensile yield strength	Mpa	≥35.0	ASTM D638, 50mm/min@23°C
Tensile strength	Mpa	≥30	
Elongation at break	%	≥25.0	
Hardness	Shore D	76~80	ASTM D2240

Remarks: The technical data above is not for specification purpose but for reference.

SinoF Hi-Tech Material Co.Ltd

Tel: 0086-28-65855299, Fax: 0086-28-87652216

E-mail: [export3@cgfkm.com](mailto:export3@cgfkm.com) [http:// www.sinofluorin.com](http://www.sinofluorin.com)